



Eupen, 23/04/2009

**TECHNICAL SPECIFICATIONS**

	Target value	Unit	tolerance	
Foam type	<b>CMHR25/</b>			
Color	<b>yellow</b>			
Width	<b>200</b>	cm	+2/+4 cm	
Height	<b>105</b>	cm	-0/+5 cm	
Density gross	<b>25,0</b>	kg/m <sup>3</sup>	+/- 5 %	
Density net	<b>23,5</b>	kg/m <sup>3</sup>	+/- 5 %	
Compression hardn.	25%	<b>40</b>	N	+/- 15 %
ISO 2439-1998	40%	<b>55</b>	N	+/- 15 %
	65%	<b>120</b>	N	+/- 15 %
Tensile strength	<b>40</b>	Kpa	min.	
ISO 1798-1997				
Elongation at break	<b>100</b>	%	min.	
ISO 1798-1997				
Compression load deflection	<b>1,40</b>	Kpa (40%)	+/- 15 %	
ISO 3386-1				
Compression set	<b>15,0</b>	%	max.	
ISO 1856-2000				
Fire behaviour	<b>BS5852 Part 2, Crib 5</b>			

Our foam types are free from CFC, HCFC and Formaldehyde.

J.-P. Doeuillet  
Qualityoffice